



## Material Data Sheet

# PLMFLON-2

### General Information

Compared with PLMFLON-1, PLMFLON-2 (polytetrafluoroethylene +15% glass fiber +5% molybdenum disulfide) has better compressive strength and sliding property. Its chemical resistance is similar to PLMFLON-1.

### Physical properties

Colour :			Gray
Hardness :	DIN EN ISO 868 (3 sec)	Shore D	63 +/-3
Density :	DIN EN ISO 1183-1	g/cm <sup>3</sup>	2.25+/-0.05
Tensile strength :	ISO 527-2	N/mm <sup>2</sup>	≥22
Elongation at break	ISO 527-1	%	≥250
Min.service temperature:	ISO 11357-2	°C	-200
Max.service temperature:	ISO 11357-2	°C	260

### Remark

All test methods and values mentioned above are corresponding to ISO or DIN standards. The properties have been determined on standardized test specimen and can not be directly related to any component or finished item. All tests are made under laboratory conditions. The mentioned values are nominal values and must be fulfilled – considering related tolerances – for each material batch.

### Suzhou Pulim Sealing Technology Co.,Ltd.

Address: No. 155 Huayang Road, Xiangcheng District, Suzhou, China, 215134  
Phone: +86 512-66333588 Fax: +86 512-66333988

Email: [sales@pulim.cn](mailto:sales@pulim.cn) [www.pulim.cn](http://www.pulim.cn)